

In the Specification

Amendments to the specification are indicated in the attached "Marked Up Version of Amendments" (page 12).

*Please replace the page 28 (Table 4), with the following page (Table 4):*

TABLE 4

Property	Test	Units	Ex 6	Ex 7	Ex 8	Ex 9	Ex 10
Specific Gravity	ASTM D1505		1.04	1.02	1.02	1.02	1.02
Melt Flow Rate	ASTM D1238	g/10 min	15.0	9.6	12.0	16.0	15.0
Tensile Strength	ASTM D638	psi	2840	2500	2300	2700	2400
Yield Strength	ASTM D638	psi	2840	3000	2600	3200	2900
Elongation	ASTM	%	200	40	150	90	80
Burn Rating 1/32"-1/8"	UL-94		V-0	V-0	V-0	V-0	V-0
Oxygen Index	ASTM D2863	%	29.0	29.0	29.0	28.0	29.0
Gardner Impact	ASTM D3029	ft-lb/in.	12.0	15.0	15.0	14.0	16.0
Izod Impact, notched	ASTM D256	ft-lb	1.1	0.9	0.8	0.7	0.9
Flexural Modulus	ASTM 790	psi	228,000	263,000	275,000	260,000	270,000
Dielectric Constant (1kHz), 23°C	ASTM D1531		2.45	2.40	2.38	2.42	2.48